



## TECHNICAL DATA

### PRODUCT DESCRIPTION: *Aerothane 101-2 Solvent Borne Epoxy Primer*

A two component solvent based epoxy coating/primer that exhibits excellent characteristics for abrasion resistance, chemical resistance, and substrate penetration. This product is suitable as a primer for high build coatings and urethane or as a stand alone coating.

### RECOMMENDED FOR:

Recommended priming or coating concrete or steel. This product can withstand exposure to many common solvents and chemicals.

### SOLIDS BY WEIGHT:

Mixed= 65% (+, - 2%)

### SOLIDS BY VOLUME:

Mixed= 52% (+, - 2%)

### VOLATILE ORGANIC CONTENT:

Part A= 3.43 pounds per gallon

Part B= 3.75 pounds per gallon

### STANDARD COLORS:

White, off white, light gray, medium gray, tile red, and beige

### RECOMMENDED FILM THICKNESS:

5-7 mils per coat wet thickness (yields 3 mils dry)

### COVERAGE PER GALLON:

240 to 300 square feet @ 5-7 mils wet thickness

### PACKAGING INFORMATION

2 gallon and 10 gallon kits (volume approx.), 2 gal kit= 1 gallon part A (8.5#/gal) (weights approximate) and 1 gal. part B (11.0#/gal) (weights approximate)

### MIX RATIO:

1 part A to 1 part B by volume

### SHELF LIFE:

1 year

### FINISH CHARACTERISTICS:

Satin gloss (30-60 at 60 degrees @ Erichsen glossmeter)

### ABRASION RESISTANCE:

Taber abrasor CS-17 calibrase wheel with 1000 gram total load and 500 cycles = 30.2 mg loss

### IMPACT RESISTANCE:

Gardner Impact, direct= 50 in. lb. (passed)

### FLEXIBILITY:

No cracks on a 1/8" mandrel

### ADHESION:

375 psi @ elcometer (concrete failure, no delamination)

### VISCOSITY:

Mixed = 300-500 cps (typical)

### DOT CLASSIFICATIONS:

Part A "FLAMMABLE LIQUID N.O.S., 3, UN1993, PGIII"

Part B "FLAMMABLE LIQUID N.O.S., 3, UN1993, PGIII"

### CURE SCHEDULE: (70°F)

pot life – 2 gallons volume .....	3-5 hours
tack free (dry to touch).....	2-4 hours
recoat or topcoat.....	4-6 hours
light foot traffic.....	16-24 hours
full cure (heavy traffic).....	2-7 days

### APPLICATION TEMPERATURE:

40-90 degrees F

### CHEMICAL RESISTANCE:

REAGENT	RATING
acetic acid 5%	A
xylene	B
mek	A
gasoline	B
10% sodium hydroxide	E
50% sodium hydroxide	D
10% sulfuric	C
10% hydrochloric acid	C
20% nitric acid	A
ethylene glycol	C

Rating key: A - not recommended, B - 2 hour term splash spill, C - 8 hour term splash spill, D - 72 hour immersion, E - long term immersion. NOTE: extensive chemical resistance information is available through your sales representative.

### PRIMER:

None required

### TOPCOAT:

Optional- Many products are suitable as topcoats including multiple coats of this product. For added chemical resistance, color stability or UV stability, topcoat with a suitable aliphatic urethane such as *Aerothane #303 High Performane Urethane*.

### LIMITATIONS:

\*Colors or gloss may be affected by high humidity, low temperatures, chemical exposure, UV exposure or lighting such as sodium vapor lights.

\*Product is not UV color stable

\*For best results use a 3/8" nap roller

\*Slab on grade requires moisture barrier

\*Substrate temperature must be 5°F above dew point

\*All new concrete must be cured for at least 30 days

\*Product color will vary from batch to batch

\*Physical properties are typical and not specifications

\*Light or bright colors (white, safety yellow, etc.) may require multiple coats or a topcoat to achieve a satisfactory hide, depending on the substrate

\*See reverse side for application instructions.

\*See reverse side for limitations of our liability and warranty.

